



ROLLMAX™
ROLLED EROSION CONTROL

Specification Sheet – EroNet™ S150® Erosion Control Blanket

DESCRIPTION

The short-term double net erosion control blanket shall be a machine-produced mat of 100% agricultural straw with a functional longevity of up to 12 months. (NOTE: functional longevity may vary depending upon climatic conditions, soil, geographical location, and elevation). The blanket shall be of consistent thickness with the straw evenly distributed over the entire area of the mat. The blanket shall be covered on the top and bottom sides with a lightweight photodegradable polypropylene netting having an approximate 0.50 x 0.50 in. (1.27 x 1.27 cm) mesh. The blanket shall be sewn together on 1.50 inch (3.81 cm) centers with degradable thread. The blanket shall be manufactured with a colored thread stitched along both outer edges (approximately 2-5 inches [5-12.5 cm] from the edge) as an overlap guide for adjacent mats.

The S150 shall meet Type 2.D specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17

Material Content

Matrix	100% Straw Fiber	0.5 lbs/sq yd (0.27 kg/sm)
Netting	Top and bottom nets: lightweight photodegradable	1.5 lbs/1000 sq ft (0.73 kg/100 sm)
Thread	Degradable	

Standard Roll Sizes

Width	6.67 ft (2.03 m)	8 ft (2.4 m)	16.0 ft (4.87 m)
Length	108 ft (32.92 m)	112 ft (34.14 m)	112 ft (34.14 m)
Weight ± 10%	40 lbs (18.14 kg)	50 lbs (22.68 kg)	100 lbs (45.36 kg)
Area	80 sq yd (66.9 sm)	100 sq yd (83.61 sm)	200 sq yd (167.22 sm)

Roughness Coefficients – Unveg.

Flow Depth	Manning's n
≤ 0.50 ft (0.15 m)	0.055
0.50 – 2.0 ft	0.055-0.021
≥ 2.0 ft (0.60 m)	0.021

Index Property	Test Method	Typical
Thickness	ASTM D6525	0.32 in. (8.13 mm)
Resiliency	ECTC Guidelines	80.5%
Water Absorbency	ASTM D1117	370%
Mass/Unit Area	ASTM D6475	8.15 oz/sy (277.1 g/sm)
Swell	ECTC Guidelines	15%
Smolder Resistance	ECTC Guidelines	Yes
Stiffness	ASTM D1388	6.06 oz-in
Light Penetration	ASTM D6567	12.4%
Tensile Strength - MD	ASTM D6818	159.6 lbs/ft (2.37 kN/m)
Elongation - MD	ASTM D6818	31.7%
Tensile Strength - TD	ASTM D6818	93.6 lbs/ft (1.39 kN/m)
Elongation - TD	ASTM D6818	26.7%
Biomass Improvement	ASTM D7322	371%

Design Permissible Shear Stress

Unvegetated Shear Stress	1.75 psf (84 Pa)
Unvegetated Velocity	6.0 fps (1.83 m/s)

NTPEP ASTM D6460 Large-Scale Channel

Unvegetated Shear Stress	2.42 psf (115.9 Pa)
Unvegetated Velocity	9.0 fps (2.75 m/s)

Slope Design Data: C Factors

Slope Length (L)	Slope Gradients (S)		
	≤ 3:1	3:1 – 2:1	≥ 2:1
≤ 20 ft (6 m)	0.004	0.106	N/A
20-50 ft	0.062	0.118	N/A
≥ 50 ft (15.2 m)	0.12	0.180	N/A

**NTPEP Large-scale Slope
ASTM D6459 - C-factor = 0.029**



North American Green
5401 St. Wendel-Cynthiana Road
Poseyville, Indiana 47633

nagreen.com
800-772-2040

©2017, North American Green is a registered trademark. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.