MATERIAL PROPERTY DATA SHEET




VMax[®] C350™

Permanent • Triple Net • Organic Fiber Matrix • Turf Reinforcement Mat

DESCRIPTION

C350 Turf Reinforcement Mat (TRM) is composed of 100% coconut fibers mechanically (stitch) bound between a three-dimensional UV stabilized, heavy duty synthetic net structure. Stitching is secured on two-inch centers using UV stabilized, synthetic thread. C350 is a permanent, three-dimensional TRM that provides immediate erosion protection and long-term turf reinforcement and is intended for applications requiring erosion protection for greater than thirty-six months.



Each roll of C350 is made in the USA and manufactured under Western Green's Quality Assurance Program to ensure a continuous distribution of fibers and consistent thickness.

Material Content			
Matrix	Coconut		
Netting	Top Net: Heavyweight, UV stable Middle Net: Corrugated Ultra-Heavyweight, UV stable Bottom Net: Heavyweight, UV stable		
Thread	Synthetic, UV Stable		

Standard Roll Sizes				
Width	8 ft	(2.4 m)	6.5 ft	(2.0 m)
Length	90 ft	(27.4 m)	55.5 ft	(17.0 m)
Weight ± 10%	74 lb	(34.0 kg)	37 lb	(17.0 kg)
Area	80 sy	(66.9 m ²)	40 sy	(33.4 m ²)

	Approvals & Classification
Classification	FHWA: Type 5.C / ECTC: 5.D
TTI Approvals	Class 2 Type H
NTPEP Number	ECP-2020-01-14

DIsclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, North American Green is a registered trademark from Western Green. Certain products and/ or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the

Index Property	Test Method	Ту	pical
Thickness	ASTM D6525	0.58 in.	(15 mm)
Mass/Unit Area	ASTM D6566	15.0 oz/sy	(500 g/sm)
Tensile Strength – MD	ASTM D6818	750 lbs/ft	(10.9 kN/m)
Tensile Strength – TD	ASTM D6818	750 lbs/ft	(10.9 kN/m)
Elongation - MD	ASTM D6818	į	30%
Elongation – TD	ASTM D6818	:	20%
UV Stability	ASTM D4355	80% (@1000 hr
Light Penetration	ASTM D6567	:	10%
Biomass Improvement	ASTM D7322	3	50%
Specific Gravity	ASTM D792	57.4 lb/ft ³	(0.92 g/cm ³)
Porosity	ECTC		N/A

Design Parameters			
Property	Unvegetated	Vegetated ³	
RUSLE C Factor ²	0.05	N/A	
Slope Maximum Gradient ¹	0.5H:1V	0.5H:1V	
Permissible Shear Stress ²	3.2 psf (155 Pa)	12.0 psf (575 Pa)	
Permissible Velocity ²	10.5 fps (3.2 m/s)	18.0 fps (5.5 m/s)	
$\tau_{_{\mathrm{veg}}}/\tau_{_{\mathrm{TRM}}}$ (HEC-15)	N/A	0.44	

Manning's n Roughness (HEC-15)			
T _{lower}	$ au_{mid}$	$ au_{ ext{upper}}$	
0.035	0.032	0.027	

- 1 Maximum Gradient a recomendation for typical installations.
- ${\small 2~Hydraulic~thresholds~compliant~with~ASTM~D6459/D6460~but~generalized~for~typical~applications.}\\$
- 3 Vegetated values dependent on established stand of vegetation

Rev. 4.2023

Scan for additional and updated product information, or click here.



