

MATERIAL PROPERTY DATA SHEET




TMAX 3K™

Permanent • 3-D Woven • UV Stable •
High Performance Turf Reinforcement Mat

DESCRIPTION

TMAX 3K is a High-Performance Turf Reinforcement Mat (HP-TRM) produced by weaving 100% UV-stabilized, high denier synthetic mono-filament yarns woven into permanent, high-strength, three-dimensional structure. The optimized properties of the material provide immediate erosion control with excellent vegetation establishment and long-term turf reinforcement. The strength, resiliency, and durability of TMAX 3K provides a decades long design life and suitability for harsh environments including debris flow and light vehicle traffic. When incorporated with high-load anchors, PP5-Pro can add strength to sub-surface soil and improve slope stability.



Material Content	
Woven, Single Layer	Green or Tan

Standard Roll Sizes				
Width	11.5 ft	(3.5 m)	8 ft	(2.4 m)
Length	78 ft	(24.0 m)	135 ft	(40.5 m)
Weight ± 10%	72 lb	(33.0 kg)	86 lb	(40 kg)
Area	100 sy	(83.6 m ²)	120 SY	(100 m ²)

Material available in custom roll sizes

Approvals & Classification	
Classification	FHWA: Type 5.C / ECTC: 5.F
TTI Approvals	Class 2 Type H
NTPEP Number	ECP-2022-01-011

Disclaimer: The information contained herein may represent product index data, performance ratings, bench scale testing or other material utility quantifications. Each representation may have unique utility and limitations. Every effort has been made to ensure accuracy, however, no warranty is claimed and no liability shall be assumed by Western Green or its affiliates regarding the completeness, accuracy or fitness of these values for any particular application or interpretation. While testing methods are provided for reference, values shown may be derived from interpolation or adjustment to be representative of intended use. For further information, please feel free to contact Western Green.

©2023, North American Green is a registered trademark from Western Green. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.

Rev. 4.2023

Scan for additional and updated product information, or [click here](#).



Index Property	Test Method	MARV	
Thickness	ASTM D6525	0.3 in.	(6 mm)
Mass/Unit Area	ASTM D6566	7.0 oz/sy	(225 g/sm)
Tensile Strength – MD	ASTM D6818	3,000 lbs/ft	(43.8 kN/m)
Tensile Strength – TD	ASTM D6818	3,000 lbs/ft	(43.8 kN/m)
Elongation - MD	ASTM D6818	25%	
Elongation – TD	ASTM D6818	25%	
UV Stability	ASTM D4355	90% @3000 hr	
UV Stability	ASTM D7238	90% @3000 hr	
Resiliency	ASTM D6524	70%	
Light Penetration	ASTM D6567	35%	
Biomass Improvement	ASTM D7322	300%	
Specific Gravity	ASTM D792	57.4 lb/ft ³	(0.92 g/cm ³)
Porosity	ECTC	96%	
Carbon Footprint	GHG*	1.3 kg CO ₂ e/m ²	

Design Parameters		
Property	Unvegetated	Vegetated ³
RUSLE C Factor ²	N/A	N/A
Slope Maximum Gradient ¹	0.5H:1V	0.5H:1V
Permissible Shear Stress ²	2.3 psf	14.0 psf (670 Pa)
Permissible Velocity ²	8.0 fps	20.0 fps (6.1 m/s)
τ_{veg} / τ_{TRM} (HEC-15)	N/A	0.35

Manning's n Roughness (HEC-15)		
τ_{lower}	τ_{mid}	τ_{upper}
0.033	0.030	0.028

¹ Maximum Gradient a recommendation for typical installations.

² Hydraulic thresholds compliant with ASTM D6459/D6460 but generalized for typical applications.

³ Vegetated values dependent on established stand of vegetation

*WRI/WBCSD Greenhouse Gas Protocol: Product Life Cycle Accounting and Reporting Standard, 2013.